



## PANAMA – 28 oz. Fabric Specifications

### Material Construction

<b>BASE FABRIC</b>	Panama Weave	Panama Weave
<b>FILAMENT SIZE</b>	1000 Denier	1000 Denier
<b>CONSTRUCTION</b>	30 x 30 inches	12 x 12 cm
<b>BASE FABRIC WEIGHT</b>	7.8 oz. / sq. yard	266 g / sq. meter
<b>FINISHED WEIGHT</b>	28 oz. / sq. yard	949 g / sq. meter
<b>WIDTH</b>	61 inches	155 cm

### Physical Properties \*

<b>GRAB TENSILE – Method 5100</b>	650 x 630 lb.	2886 x 2886 N
<b>STRIP TENSILE – Method 5102</b>	465 x 300 lb.	2065 x 1554 N
<b>TONGUE TEAR – Method 5134</b>	150 x 130 lb.	665 x 577 N
<b>TRAPEZOID TEAR – Method 5136</b>	125 x 95 lb.	555 x 422 N
<b>ADHESION - In-House (Force/2 cm)</b>	15 lb.	67 N

<b>COLD CRACK -</b>	<b>Method 5874 @</b> -58 degrees F -50 degrees C	<b>No Cracking or Flaking</b>
---------------------	--	-------------------------------

<b>HIGH TEMPERATURE RANGE</b>	110 – 120 degrees C. 230 – 248 degrees F.
-------------------------------	--

\*Property analysis performed according to Federal Test Method Standard 191A. The above information is provided to aid with regards to any experimentation. It is offered as a guide only and we assume no liability with results.